



mechanical properties

Wire diameter	CARBON	Min tensile strength	MAX tensile strength
1,20	42-46	180	195
1,30	42-46	175	185
1,40	42-46	170	180
1,20	62-65	210	225
1,30	62-65	205	220
1,40	62-65	200	215
1,50	62-65	195	210
1,60	62-65	185	195
1,70	62-65	183	190
1,80	62-65	180	190
1,90	62-65	178	188
2,00	62-65	176	186
2,00	62-65	174	180
2,10	63-66	180	185
2,20	63-66	165	175
2,30	65-68	164	173
2,38	66-68	162	170
2,40	66-68	162	170
2,80	66-68	152	162
3,00	66-68	152	162
3,50	66-68	152	162
3,80	68-70	152	162
4,00	68-70	152	162